

Technical Data Sheet



<i>Product</i>	Mercury Chrome
<i>Codes</i>	BWA0001
<i>Use</i>	A very bright aluminium basecoat with fine particle size and dark flop effect.
<i>Mix</i>	Ready for use.
<i>Preparation</i>	Ensure all surfaces to be coated are dry and free from any contamination. To achieve maximum results, the primer needs to be smooth and glossy.
<i>Application</i>	Use conventional spray application to a dry film thickness of 5-15 microns typically in 2 coats with a 2 minute flash off between coats. Flash off for 10 minutes before overcoating.
<i>cure</i>	Product can be cured up to 200'C depending on the clearcoat used. If using powder clearcoat, fully bake the basecoat for 20 mins at 160'C substrate temperature.
<i>Health and Safety</i>	Always read and understand the appropriate MSDS before proceeding.

Always check colour and finish before proceeding. Jaytees strive to ensure all information about the product is correct however we have no control over application conditions or equipment. Therefore we cannot accept liability for the performance of the product in service or any loss or damage arising out of use unless agreed in writing prior to use.