Technical Data Sheet



Product	2K Fast DTM Non-Iso Light Anthracite Topcoat				
Codes	DTM1034C	DTM1034A	DTM1034T		
Use	Top-coat especially for direct to metal applications such as diamond cut alloy wheels. Has excellent adhesion, long pot-life and contains no isocyanates				
Mix	or 1:1 DTM1034C:DTM1 For example mixes see b	L034C:DTM1034A:DTM103 .034A + 50% DTM1034T by pelow. To achieve the corre ratio. Pot/use life is 7 hours	volume. ct finish and gloss it is vitally important	to use	

*Total mixed paint re	90ml	180ml	300ml	
	DTM1034C DTM1034A DTM1034T			100ml 100ml 100ml

Preparation	Ensure all surfaces to be coated are dry and free from any grease and other contamination. We strongly advise using Jaytees Preparation Wipe TS0028			
Application	Shake cans well before use. Use conventional spray application. to a dry film thickness of 20-30 microns in two coats. Flash off for 2 mins between coats. Apply drop-coat immediately after second coat if required for colour. We recommend a substrate temperature between 15 and 25°C. Flash off for 5 mins before curing.			
Cure	Cure for 15-20 mins at 60°C substrate temperature. IR Curing: 10-15 mins minimum @20cm distance using 1KW lamp. Allow to cool to ambient temperarure before exposing to external enviroment.			
Coverage	12.1m ² per mixed litre (assuming 100% transfer efficiency) @25 micron dry film thickness			
Health and Safety	Always read and understand the appropriate MSDS before proceeding.			
Storage	Store in cool dry cconditions in original packaging. When not in use keep lids	nditions in original packaging. When not in use keep lids tightly closed.		
	Always check colour and finish before proceeding. Jaytees strive to ensure all information about the product is correct however we have no control over application conditions or equipment. Therefore we cannot accept liability for the performance of the product in service or any loss or damage arising out of use unless agreed in writing prior to use.	9.10.23 REV 1		