

Technical Data Sheet



Product 2K Fast DTM Non-Iso Coarse Silver Topcoat

Codes DTM1036C DTM1036A DTM1036T

Use Top-coat especially for direct to metal applications such as diamond cut alloy wheels. Has excellent adhesion, long pot-life and contains no isocyanates

Mix Mix ratio is 1:1:1 DTM1036C:DTM1036A:DTM1036T* by volume.
or 1:1 DTM1036C:DTM1036A + 50% DTM1036T by volume.
For example mixes see below. To achieve the correct finish and gloss it is vitally important to use the recommended mix ratio. Pot/use life is 7 hours minimum at 20°C.

*Total mixed paint required	90ml	180ml	300ml
	DTM1036C 30ml	60ml	100ml
	DTM1036A 30ml	60ml	100ml
	DTM1036T 30ml	60ml	100ml

Preparation Ensure all surfaces to be coated are dry and free from any grease and other contamination. **We strongly advise using Jaytees Preparation Wipe TS0028**

Application Shake cans well before use.
Use conventional spray application.
to a dry film thickness of 20-30 microns in two coats. Flash off for 2 mins between coats.
Apply drop-coat immediately after second coat if required for colour.
We recommend a substrate temperature between 15 and 25°C.
Flash off for 5 mins before curing.

Cure Cure for 15-20 mins at 60°C substrate temperature.
IR Curing: 10-15 mins minimum @20cm distance using 1KW lamp. Allow to cool to ambient temperature before exposing to external environment.

Coverage 12.0m² per mixed litre (assuming 100% transfer efficiency) @25 micron dry film thickness

Health and Safety Always read and understand the appropriate MSDS before proceeding.

Storage Store in cool dry conditions in original packaging. When not in use keep lids tightly closed.

Always check colour and finish before proceeding. Jaytees strive to ensure all information about the product is correct however we have no control over application conditions or equipment. Therefore we cannot accept liability for the performance of the product in service or any loss or damage arising out of use unless agreed in writing prior to use.

9.10.23

REV 1